

	C	ONFOR	MITY CE	ERTIFICA	TE			
Ground Granulated Blastfurnace Slag Pro Samp				oduced at	Aboño		Works	
				ole Period	May 2	2020		
Certificate of Conformity of GGBS to EN 15167-1:2006				Certificate of Conformity of Combinations of GGBS and CEM I Portland Cement to				
Spot samples of GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1:2006 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.				Annex A of BS 8500-2:2015 Portland Cement Source:				
				Cimpor				
Aboño GGBS Only				For combinations of GGBS supplied from the above works with the above CEM I Portland cement the permitted				
Results		Product			proportions conforming to the requirements given in			
Fineness m²/kg		465	min. 275	annex A of BS 8500-2:2015 are:				
Magnesium Oxide MgO %		8	max. 18	S	Strength	Not Less	Not More	
Sulfate SO ₃ %		0.1	max. 2.5		Class	Than**	Than**	
Sulfide S ²⁻ %		0.7	max. 2.0		52.5L	6	33	
Chloride Content Cl ⁻ %		0.03	max. 0.10		42.5L	6	63	
Moisture Content %		0.0	max. 1.0		32.5L	52	79	
Corrected Loss on Ignition %		1.3	max. 3.0					
Aluminium Oxide Al ₂ O ₃ %		12.6	to 1 d.p.	Conformity Evaluation Period (if less than 6 months)		N/A	month(s)	
Note: If the value of Al_2O_3 is $\ge 14.5\%$ the '+SR' restriction will			·					
be exceeded if the C ₃ A of the CEM I is >10%. Alkalis as Na ₂ O equ. (acid soluble)				Combination Designation				
	bie) ≤ 1.0		,	(Table 1 BS 8500-2:2015)				
Guaranteed Alkali limit % Certified Average Alkali (Last 25) %		0.55			CIIA-S CIIB-S	6 21	20 35	
Declared Mean: Mean last 25 + (SD last 25 x 1.64) %		0.60			CIIIA	36	65	
COMBINATION OF 50% LABORATOR					CIIIB	66	80	
CEM I PORTLAND CEMENT AND 50% GGBS				J		GGBS		
Initial Setting Time min		240	not > than 2 x PC	Results of tests in accordance with BS EN 196-1 for 50% GGBS combination with 50% CEM I Portland cement shown above				
Activity Index %	7 days	61	min. 45	COMMONTO	oombination with 60% OEM 11 ordana domain driew			
	28 days	91	min. 70		Age	7 Days	28 Days	
LABORATORY STOCK CEM I PORTLAND CEMENT ONLY			Compressiv	e Strength N/mm ²	28.0	50.7		
The stock CEM I Portland cement used in these tests was supplied by CEMENTOS TUDELA VEGUIN, S.A and the following results were obtained from that sample				The samples of LKAB Minerals GGBS and the CEM I Portland cement were bulk average monthly samples for the works specified				
Initial Setting Time min		185						
Compressive Strength N/mm ²	7 days 28 days	48.7 57.0				ϵ		
i ne ఆఆടാ contained no additional materials other than those permitted. The above results and other tests demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1:2006.								
LKAB MInerals Ltd are acting as a dispatching of and further detals and certification			above GGBS		0099/CPF	R/B34/0001		

Signed: