



CONFORMITY CERTIFICATE																																				
Ground Granulated Blastfurnace Slag Produced at		Aboño																																		
Sample Period		May 2020																																		
Certificate of Conformity of GGBS to EN 15167-1:2006		Certificate of Conformity of Combinations of GGBS and CEM I Portland Cement to Annex A of BS 8500-2:2015																																		
Spot samples of GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1:2006 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.		Portland Cement Source:																																		
Aboño GGBS Only		Rugby																																		
For combinations of GGBS supplied from the above works with the above CEM I Portland cement the permitted proportions conforming to the requirements given in annex A of BS 8500-2:2015 are:		<table border="1"> <thead> <tr> <th>Strength Class</th> <th>Not Less Than**</th> <th>Not More Than**</th> </tr> </thead> <tbody> <tr> <td>52.5L</td> <td>6</td> <td>25</td> </tr> <tr> <td>42.5L</td> <td>6</td> <td>65</td> </tr> <tr> <td>32.5L</td> <td>43</td> <td>80</td> </tr> <tr> <td>Conformity Evaluation Period (if less than 6 months)</td> <td>N/A</td> <td>month(s)</td> </tr> <tr> <td>Combination Designation (Table 1 BS 8500-2:2015)</td> <td colspan="2"></td> </tr> <tr> <td>CIIA-S</td> <td>6</td> <td>20</td> </tr> <tr> <td>CIIB-S</td> <td>21</td> <td>35</td> </tr> <tr> <td>CIIIA</td> <td>36</td> <td>65</td> </tr> <tr> <td>CIIBB</td> <td>66</td> <td>80</td> </tr> <tr> <td colspan="3" style="text-align: right;">** % GGBS</td> </tr> </tbody> </table>		Strength Class	Not Less Than**	Not More Than**	52.5L	6	25	42.5L	6	65	32.5L	43	80	Conformity Evaluation Period (if less than 6 months)	N/A	month(s)	Combination Designation (Table 1 BS 8500-2:2015)			CIIA-S	6	20	CIIB-S	21	35	CIIIA	36	65	CIIBB	66	80	** % GGBS		
Strength Class	Not Less Than**	Not More Than**																																		
52.5L	6	25																																		
42.5L	6	65																																		
32.5L	43	80																																		
Conformity Evaluation Period (if less than 6 months)	N/A	month(s)																																		
Combination Designation (Table 1 BS 8500-2:2015)																																				
CIIA-S	6	20																																		
CIIB-S	21	35																																		
CIIIA	36	65																																		
CIIBB	66	80																																		
** % GGBS																																				
<table border="1"> <thead> <tr> <th>Results</th> <th>Product</th> <th>EN Limit</th> </tr> </thead> <tbody> <tr> <td>Fineness m²/kg</td> <td>465</td> <td>min. 275</td> </tr> <tr> <td>Magnesium Oxide MgO %</td> <td>8</td> <td>max. 18</td> </tr> <tr> <td>Sulfate SO₃ %</td> <td>0.1</td> <td>max. 2.5</td> </tr> <tr> <td>Sulfide S²⁻ %</td> <td>0.7</td> <td>max. 2.0</td> </tr> <tr> <td>Chloride Content Cl⁻ %</td> <td>0.03</td> <td>max. 0.10</td> </tr> <tr> <td>Moisture Content %</td> <td>0.0</td> <td>max. 1.0</td> </tr> <tr> <td>Corrected Loss on Ignition %</td> <td>1.3</td> <td>max. 3.0</td> </tr> <tr> <td>Aluminium Oxide Al₂O₃ %</td> <td>12.6</td> <td>to 1 d.p.</td> </tr> </tbody> </table>		Results	Product	EN Limit	Fineness m ² /kg	465	min. 275	Magnesium Oxide MgO %	8	max. 18	Sulfate SO ₃ %	0.1	max. 2.5	Sulfide S ²⁻ %	0.7	max. 2.0	Chloride Content Cl ⁻ %	0.03	max. 0.10	Moisture Content %	0.0	max. 1.0	Corrected Loss on Ignition %	1.3	max. 3.0	Aluminium Oxide Al ₂ O ₃ %	12.6	to 1 d.p.	Results of tests in accordance with BS EN 196-1 for 50% GGBS in combination with 50% CEM I Portland cement shown above							
Results	Product	EN Limit																																		
Fineness m ² /kg	465	min. 275																																		
Magnesium Oxide MgO %	8	max. 18																																		
Sulfate SO ₃ %	0.1	max. 2.5																																		
Sulfide S ²⁻ %	0.7	max. 2.0																																		
Chloride Content Cl ⁻ %	0.03	max. 0.10																																		
Moisture Content %	0.0	max. 1.0																																		
Corrected Loss on Ignition %	1.3	max. 3.0																																		
Aluminium Oxide Al ₂ O ₃ %	12.6	to 1 d.p.																																		
Note: If the value of Al ₂ O ₃ is ≥ 14.5% the '+SR' restriction will be exceeded if the C ₃ A of the CEM I is >10%.		<table border="1"> <thead> <tr> <th>Age</th> <th>7 Days</th> <th>28 Days</th> </tr> </thead> <tbody> <tr> <td>Compressive Strength N/mm²</td> <td>26.7</td> <td>49.1</td> </tr> </tbody> </table>		Age	7 Days	28 Days	Compressive Strength N/mm ²	26.7	49.1																											
Age	7 Days	28 Days																																		
Compressive Strength N/mm ²	26.7	49.1																																		
Alkalis as Na ₂ O equ. (acid soluble)		<i>The samples of LKAB Minerals GGBS and the CEM I Portland cement were bulk average monthly samples for the works specified</i>																																		
<table border="1"> <tbody> <tr> <td>Guaranteed Alkali limit %</td> <td>≤ 1.0</td> <td></td> </tr> <tr> <td>Certified Average Alkali (Last 25) %</td> <td>0.55</td> <td></td> </tr> <tr> <td>Declared Mean : Mean last 25 + (SD last 25 x 1.64) %</td> <td>0.60</td> <td></td> </tr> </tbody> </table>		Guaranteed Alkali limit %	≤ 1.0		Certified Average Alkali (Last 25) %	0.55		Declared Mean : Mean last 25 + (SD last 25 x 1.64) %	0.60		CE																									
Guaranteed Alkali limit %	≤ 1.0																																			
Certified Average Alkali (Last 25) %	0.55																																			
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %	0.60																																			
COMBINATION OF 50% LABORATORY STOCK CEM I PORTLAND CEMENT AND 50% GGBS		0099/CPR/B34/0001																																		
<table border="1"> <tbody> <tr> <td>Initial Setting Time min</td> <td>240</td> <td>not > than 2 x PC</td> </tr> <tr> <td rowspan="2">Activity Index %</td> <td>7 days</td> <td>61</td> </tr> <tr> <td>28 days</td> <td>91</td> </tr> </tbody> </table>		Initial Setting Time min	240	not > than 2 x PC	Activity Index %	7 days	61	28 days	91	<i>The stock CEM I Portland cement used in these tests was supplied by CEMENTOS TUDELA VEGUIN, S.A and the following results were obtained from that sample</i>																										
Initial Setting Time min	240	not > than 2 x PC																																		
Activity Index %	7 days	61																																		
	28 days	91																																		
LABORATORY STOCK CEM I PORTLAND CEMENT ONLY		<table border="1"> <tbody> <tr> <td>Initial Setting Time min</td> <td>185</td> <td></td> </tr> <tr> <td rowspan="2">Compressive Strength N/mm²</td> <td>7 days</td> <td>48.7</td> </tr> <tr> <td>28 days</td> <td>57.0</td> </tr> </tbody> </table>		Initial Setting Time min	185		Compressive Strength N/mm ²	7 days	48.7	28 days	57.0																									
Initial Setting Time min	185																																			
Compressive Strength N/mm ²	7 days	48.7																																		
	28 days	57.0																																		
<i>The GGBS contained no additional materials other than those permitted. The above results and other tests demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1:2006.</i>		LKAB Minerals Ltd are acting as a dispatching centre in the distribution of the above GGBS and further details and certification are available on request																																		

Signed:

L Bontoft - Technical Manager GGBS