




CONFORMITY CERTIFICATE					
Ground Granulated Blastfurnace Slag Produced at			Scunthorpe		
Sample Period			May 2019		
Works					
Certificate of Conformity of GGBS to EN 15167-1:2006			Certificate of Conformity of Combinations of GGBS and CEM I Portland Cement to Annex A of BS 8500-2:2015		
Spot samples of GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1:2006 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.			Portland Cement Source: Rugby		
Scunthorpe GGBS Only			For combinations of GGBS supplied from the above works with the above CEM I Portland cement the permitted proportions conforming to the requirements given in annex A of BS 8500-2:2015 are:		
Results	Product	EN Limit	Strength Class	Not Less Than**	Not More Than**
Fineness m ² /kg	515	min. 275	52.5L	6	21
Magnesium Oxide MgO %	9	max. 18	42.5L	6	56
Sulfate SO ₃ %	0.4	max. 2.5	32.5L	43	73
Sulfide S ²⁻ %	0.8	max. 2.0			
Chloride Content Cl ⁻ %	0.01	max. 0.10	Conformity Evaluation Period (if less than 6 months)	N/A	month(s)
Moisture Content %	0.1	max. 1.0	Combination Designation (Table 1 BS 8500-2:2015)		
Corrected Loss on Ignition %	1.3	max. 3.0	CIIA-S	6	20
Aluminium Oxide Al ₂ O ₃ %	12.8	to 1 d.p.	CIIB-S	21	35
Note: If the value of Al ₂ O ₃ is ≥ 14.5% the '+SR' restriction will be exceeded if the C ₃ A of the CEM I is >10%.			CIIIA	36	65
<i>Alkalis as Na₂O equ. (acid soluble)</i>			CIIB	66	80
Guaranteed Alkali limit %	≤ 1.0		** % GGBS		
Certified Average Alkali (Last 25) %	0.70		<i>Results of tests in accordance with BS EN 196-1 for 50% GGBS in combination with 50% CEM I Portland cement shown above</i>		
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %	0.79		Age	7 Days	28 Days
COMBINATION OF 50% LABORATORY STOCK CEM I PORTLAND CEMENT AND 50% GGBS			Compressive Strength N/mm ²	29.8	49.1
Initial Setting Time min.	235	not > than 2 x PC	<i>The samples of LKAB Minerals GGBS and the CEM I Portland cement were bulk average monthly samples for the works specified</i>		
Activity Index %	7 days	64			
	28 days	85			
LABORATORY STOCK CEM I PORTLAND CEMENT ONLY					
<i>The stock CEM I Portland cement used in these tests was supplied by Hanson Ribblesdale works and the following results were obtained from that sample</i>					
Initial Setting Time min	180				
Compressive Strength N/mm ²	7 days	48.5			
	28 days	60.2			
The GGBS contained no additional materials other than those permitted. The above results and other tests demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1:2006					

Signed: 