



CONFORMITY CERTIFICATE

Ground Granulated Blastfurnace Slag Produced at **Scunthorpe** Works
 Sample Period **January 2020**

Certificate of Conformity of GGBS to EN 15167-1:2006

Spot samples of GGBS were taken and tested to determine conformity to the autocontrol requirements of EN 15167-1:2006 "Ground granulated blastfurnace slag for use in concrete, mortar and grout" following the methods given in that standard. The values reported are mean values for the monthly production period.

Scunthorpe GGBS Only

Results	Product	EN Limit
Fineness m ² /kg	521	min. 275
Magnesium Oxide MgO %	8	max. 18
Sulfate SO ₃ %	0.2	max. 2.5
Sulfide S ²⁻ %	0.8	max. 2.0
Chloride Content Cl ⁻ %	0.03	max. 0.10
Moisture Content %	0.0	max. 1.0
Corrected Loss on Ignition %	1.0	max. 3.0
Aluminium Oxide Al ₂ O ₃ %	12.6	to 1 d.p.

Note: If the value of Al₂O₃ is ≥ 14.5% the '+SR' restriction will be exceeded if the C₃A of the CEM I is >10%.

Alkalis as Na₂O equ. (acid soluble)

Guaranteed Alkali limit %	≤ 1.0	
Certified Average Alkali (Last 25) %	0.62	
Declared Mean : Mean last 25 + (SD last 25 x 1.64) %	0.70	

COMBINATION OF 50% LABORATORY STOCK CEM I PORTLAND CEMENT AND 50% GGBS

Initial Setting Time min.	220	not > than 2 x PC
Activity Index %	7 days	72 min. 45
	28 days	94 min. 70

LABORATORY STOCK CEM I PORTLAND CEMENT ONLY

The stock CEM I Portland cement used in these tests was supplied by Hanson Ribblesdale works and the following results were obtained from that sample

Initial Setting Time min	180	
Compressive Strength N/mm ²	7 days	46.6
	28 days	56.2

The GGBS contained no additional materials other than those permitted. The above results and other tests demonstrate the conformity of the material sold during the month to the requirements of EN 15167-1:2006

Certificate of Conformity of Combinations of GGBS and CEM I Portland Cement to Annex A of BS 8500-2:2015

Portland Cement Source:

Dunbar

For combinations of GGBS supplied from the above works with the above CEM I Portland cement the permitted proportions conforming to the requirements given in annex A of BS 8500-2:2015 are:

Strength Class	Not Less Than**	Not More Than**
52.5L	6	31
42.5L	6	53
32.5L	41	80
Conformity Evaluation Period (if less than 6 months)	N/A	month(s)
Combination Designation (Table 1 BS 8500-2:2015)		
CIIA-S	6	20
CIIB-S	21	35
CIIIA	36	65
CIIBB	66	80

** % GGBS

Results of tests in accordance with BS EN 196-1 for 50% GGBS in combination with 50% CEM I Portland cement shown above

Age	7 Days	28 Days
Compressive Strength N/mm ²	20.7	47.6

The samples of LKAB Minerals GGBS and the CEM I Portland cement were bulk average monthly samples for the works specified



1333-CPR-00194

Signed: