

Gypsol Summit

Gypsol Summit is designed specifically for use in high rise applications where the screed needs to be pumped to ten storeys and above.

About Gypsol Summit

Gypsol Binder is an integral component of Gypsol Summit, a screed suitable for use in all construction types including steel frame, concrete frame, lightweight steel and traditional masonry construction. It is suitable for residential and commercial properties, Gypsol Summit can be used to improve the acoustic performance of a floor to meet or exceed Part E of building regulations. Gypsol Summit has been specially formulated to allow pumping to high levels over 10 stories.

Physical data

Appearance	Off white fluid mortar
Density (kg/m ³)	Wet – 2200 Dry - 2000
Required flow (EN 13454-2)	230-270mm
Minimum strength	C25-F4
Reaction to fire	Class A1 _n Non-Combustible

Performance data

Working time	Place and finish within 3 hours of batching
Foot traffic	24-48 hours
Loading	7 days
Drying (50mm depth) ^[1]	At 20°C and 60% RH - 28 days
Force drying	Can be force dried after 7 days

Please refer to our post installation guidance document for further details

LKAB Minerals Ltd are not screed manufacturers. The chemical and physical data are expected average figures and are given in good faith but without guarantee. The only warranty LKAB Minerals makes is the express written warranty extended on the sale of its products. For manufacturer specific data please contact your Gypsol screed supplier. Gypsol screeds should be installed in accordance with BS 8204-7:2003 by suitably trained and experienced installers. Gypsol Summit Data Sheet, 08-02 EN, 26-02

Minimum depth requirements

Bonded	25mm ^[2]
Unbonded	30mm
Floating	35mm domestic 40mm commercial
Acoustic	80kg/m ² @ 40mm
Cover to conduits	25mm

[2] Prepare the substrate in accordance with BS8204:7:2003 using a gritted two coat epoxy resin DPM or similar.

Bay sizes and joint requirements

Heated

Maximum length	20m
Maximum aspect ratio	6:1
Maximum bay size	300m ²

Movement joints should be placed at door thresholds, between independently controlled heating zones and where heated and unheated screeds meet.

Unheated

Maximum length	40m
Maximum aspect ratio	8:1
Maximum bay size	1000m ²

Environmental data

Typical embodied CO ₂	2.5-7.5kg/m ²
Thermal Conductivity	Up to 2.3w/mK